



# Midwest Construction Products

## GFNW3.5

**Midwest Construction Products GFNW3.5** is a needle-punched nonwoven geotextile made of 100% polypropylene staple fibers, which are formed into a random network for dimensional stability. **GeoForce Non Woven 3.5** resists ultraviolet deterioration, rotting, biological degradation, naturally encountered basics and acids. Polypropylene is stable within a pH range of 2 to 13. **GFNW3.5** conforms to the physical values listed below:

PROPERTY	TEST METHOD	UNIT	M.A.R.V. (Minimum Average Roll Value)
<b>Weight (Typical)</b>	ASTM D5261	oz/yd <sup>2</sup> (g/m <sup>2</sup> )	3.5 (119)
<b>Grab Tensile</b>	ASTM D4632	lbs (kN)	90 (.401)
<b>Grab Elongation</b>	ASTM D4632	%	50
<b>Trapezoid Tear Strength</b>	ASTM D4533	lbs (kN)	40 (.178)
<b>Puncture Resistance</b>	ASTM D4833	lbs (kN)	60 (.267)
<b>Mullen Burst</b>	ASTM D3786	psi (kPa)	185 (1275)
<b>Permittivity*</b>	ASTM D4491	sec <sup>-1</sup>	2.2
<b>Water Flow*</b>	ASTM D4491	gpm/ft <sup>2</sup> (l/min/m <sup>2</sup> )	150 (6095)
<b>A.O.S.*</b>	ASTM D4751	U.S. Sieve (mm)	50 (0.3)
<b>U.V. Resistance</b>	ASTM D4355	%/hrs	70/500

\*At the time of manufacturing. Handling, storage, and shipping may change these properties.

PACKAGING	
<b>Roll Dimension (W x L) - Ft</b>	12.5x360/15 x 300
<b>Square Yards per Roll</b>	500
<b>Estimated Roll Weight - lbs</b>	140

\* At the time of manufacturing. Handling may change these properties.

This information is provided for reference purposes only and is not intended as a warranty or guarantee. Midwest Construction Products assumes no liability in connection with the use of this information.

For further information please call 800-532-2381

[www.midwestconstruct.com](http://www.midwestconstruct.com)